

# H110MAS

## HOMOPOLYMER

### FOR INJECTION MOLDED PRODUCTS

Repol H110MAS is a nucleated PP homopolymer grade recommended for Injection Molding processes. It offers a unique combination of high crystallization temperature in the polymer and isotropic shrinkage in the final product. This blend enhances production rates across various applications.

In addition, H110MAS exhibits higher flexural modulus and surface gloss, facilitating the molding of high-quality parts by minimizing warpage, sink marks, and other molding defects.

**BIS Designation Code: IS 10951-1-MBL-C**

#### Typical Characteristics

Property	Test Method	Unit	Typical Value*
Melt Flow Rate (230°C/2.16 kg)	ASTM D1238	g/10 min	11
Density	ASTM D792	g/cc.	0.90
Tensile Strength at Yield (50 mm/min.)	ASTM D638	MPa	38
Elongation at Yield (50 mm/min.)	ASTM D638	%	10
Flexural Modulus (1% Secant)	ASTM D790A	MPa	1650
Notched Izod Impact Strength (23 °C.)	ASTM D256	J/m	30
Heat Deflection Temperature (455 KPa)	ASTM D648	°C	110
Hardness – Shore D	ASTM D2240	---	71

\* Typical values, not to be taken as specification. All the mechanical properties as per ASTM D638 injection molded Type 1 specimen in accordance with ASTM D4101

#### Typical Processing Conditions

Melt temperature: 200 – 250 °C

Mold temperature: 20 – 50 °C

Note: Processing parameters mentioned above are for reference only and not to be considered as specifications. They may vary based on the product to be manufactured.

#### Applications

Injection molded articles for rigid packaging, furniture & houseware.

### Regulatory Information

The product complies with Indian Standard IS 10910 on “Specification for polypropylene and its copolymers for safe use in contact with foodstuffs, pharmaceuticals and drinking water. It also conforms to IS 16738:2018 on positive list of constituents for polypropylene, polyethylene and their copolymers for its safe use in contact with foodstuffs and pharmaceuticals. The grade and the additives incorporated in it also comply with FDA:CFR Title 21,177.1520, Olefin polymers.

Not to be used in the manufacture of Single Use Plastic (SUP) items prohibited under PWM Rules, 2016.

### Storage Recommendations

Bags should be stored in dry / closed conditions at temperatures below 50°C and protected from UV / direct sunlight