



# H350FH

## HOMOPOLYMER

FOR FIBER & FILAMENT AND NON-WOVEN

Repol H350FH is PP homopolymer grade recommended for use in fiber & filaments and spun bond non-woven. It is suitable for high speed spinning of fine denier fibers and low GSM non-woven fabrics. The grade is specially formulated for Anti Gas Fading properties.

**BIS Designation Code: IS 10951-1-CB-E**

### Typical Characteristics

Property	Test Method	Unit	Typical Value*
Melt Flow Rate (230°C/2.16 kg)	ASTM D1238	g/10 min	38
Density	ASTM D792	g/cc.	0.90
Tensile Strength at Yield (50 mm/min.)	ASTM D638	MPa	34
Elongation at Yield (50 mm/min.)	ASTM D638	%	10
Flexural Modulus (1% Secant)	ASTM D790A	MPa	1550
Notched Izod Impact Strength (23 °C.)	ASTM D256	J/m	22
Heat Deflection Temperature (455 KPa)	ASTM D648	°C	104
Hardness – Shore D	ASTM D2240	---	70

\* Typical values, not to be taken as specification. All the mechanical properties as per ASTM D638 injection molded Type 1 specimen in accordance with ASTM D4101

### Typical Processing Conditions

Extrusion Temperature: 180 – 260 °C

Note: Processing parameters mentioned above are for reference only and not to be considered as specifications. They may vary based on the product to be manufactured.

### Applications

POY, FDY & Crimped filament yarns, Spun-bond nonwoven fabrics for Filtration, Hygiene & Medical Disposables, Packaging and Agriculture.

### Regulatory Information

The product complies with Indian Standard IS 10910 on “Specification for polypropylene and its copolymers for safe use in contact with foodstuffs, pharmaceuticals and drinking water. It also conforms to IS 16738:2018 on positive list of constituents for polypropylene, polyethylene and their copolymers for its safe use in contact with foodstuffs and pharmaceuticals. The grade and the additives incorporated in it also comply with FDA : CFR Title 21,177.1520, Olefin polymers. Not to be used in the manufacture of Single Use Plastic (SUP) items prohibited under PWM Rules, 2016.

### Storage Recommendations

Bags should be stored in dry / closed conditions at temperatures below 50°C and protected from UV / direct sunlight