



LL20FS020 LL20FA020

LINEAR LOW DENSITY POLYETHYLENE FILM EXTRUSION GRADE

This is butene based Linear Low Density Polyethylene grade with Optimum level of Antioxidants and is designed for good processing on Blown and Cast Film lines with balanced mechanical & optical Properties

LL20FS020: With Slip & Anti block

LL20FA020: Without Slip & Anti block

Typical Characteristics*			
Property	Test Method	Unit	Typical Value**
Melt Flow Index (190°C / 2.16 Kg)	ASTM D 1238	g/10 min.	2.0
Density (23°C)	ASTM D 1505	g/cm ³	0.918
Tensile Strength at Break (MD / TD)	ASTM D 882	Kg/cm ³	300 / 200
Elongation at Break (MD / TD)	ASTM D 882	%	800 / 950
Tear Strength (MD / TD)	ASTM D 1922	g/μm	2.5 / 7.5
Dar Drop Impact (F-50)	ASTM D 1922	g/ μm	2.1
Haze	ASTM D 1003	%	16

* Typical characteristics and not to be taken as specifications

** Typical values of 40 μ film made with 1.8 mm die gap & 2.25 BUR on LL20FA020

APPLICATIONS:

Blown & Cast Films. For Co extrusion, Lamination, Mulch films for Agriculture, Shopping bags, Liners, Protection films, Bubble wrap films & other packaging films.

Regulatory Information

- Meets the requirement stipulated in standard IS: 10146 on "Specification for Polyethylene for safe use in contact with foodstuff, pharmaceutical, and drinking water". It also conforms to the positive list of constituents as prescribed in IS: 10141. The grade and the additives incorporated in it also comply with the FDA:CFR Title 21,177,1520, Olefin polymers

Storage Recommendations

- Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV / direct sunlight.

Reliance Industries Limited