



F60003

HIGH DENSITY POLYETHYLENE Use in blends in Blown, Coextruded, oriented films

F60003 is a High Density Polyethylene grade suitable for use in blends in coextruded oriented film application. This grade is designed to improve stiffness and barrier requirement in films. This resin offers good balance of mechanical and optical properties.

TYPICAL CHARACTERISTICS*

PROPERTY	TEST METHOD	UNIT	TYPICAL VALUE
Density (23°C)	ASTM D 1505	g/cc	0.958
Melt Flow Index (190°C / 2.16 Kg)	ASTM D 1238	g/10 min.	0.7
Film Properties**			
Tensile Strength at Yield (MD / TD)	ASTM D 882	MPa	29.0/26.0
Ultimate Tensile Strength (MD / TD)	ASTM D 882	MPa	45.0/40.0
Elongation at Break (MD / TD)	ASTM D 882	%	780 /950
Dart Impact Strength, F50 (38 mm dart, 66 cm height)	ASTM D 1709	g/ mic.	1.8
Tear Strength (MD / TD)	ASTM D 1922	g/μm	0.4 /4.5

* Typical characteristics and not to be taken as specifications

** Typical properties measured on 40 μm film made with 0.8 mm die gap & 2.7 BUR

APPLICATIONS:

Used for producing blown film, coextruded films and is recommended for use in food packaging, films for e-commerce application and packaging applications.

Regulatory Information

- This grade meets the requirements stipulated in IS 7328:2020, "Specification For Polyethylene Material For Moulding And Extrusion" and it's subsequent amendments, when the products are used in contact with foodstuffs, pharmaceuticals and drinking water. It also conforms to IS 16738:2018 "Positive List of Constituents for Polypropylene, Polyethylene and their Copolymers for its Safe Use in Contact with Foodstuffs and Pharmaceuticals"
- The grade and the additives incorporated in it also comply with the FDA: CFR Title 21,177.1520, Olefin polymers
- BIS Designation Code : IS 7328-3B-FB-GDA.
- Not to be used in the manufacture of Single Use Plastic (SUP) items prohibited under PWM Rules, 2016.

Storage Recommendations

- Bags should be stored in dry/closed conditions at temperatures below 50°C and protected from UV / direct sunlight.