

Technical Data Sheet

Maywoflamm[®] ECE

ABS

Typical characteristics

- Flame retardant
- Base Material: ABS

Typical industries

- Vehicle Construction
- Bus
- Vacuum Forming

	Test method	Unit	Guideline value
General properties			
Density	DIN EN ISO 1183-1	g / cm ³	1,16
Flammability	ECE R118		Annex 6, 7, 8 (1,5-7,0mm)
Mechanical properties			
Yield stress	DIN EN ISO 527	MPa	26
Elongation at break	DIN EN ISO 527	%	32
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1889
Notched impact strength	DIN EN ISO 179	kJ / m ²	6
Thermal properties			
Melting temperature	ISO 11357-3	°C	>180
Thermal conductivity	DIN 52612-1	W / (m * K)	0,2
Coefficient of linear thermal expansion	DIN 53752	10 ⁻⁶ / K	90
Service temperature, long term	Average	°C	80
Service temperature, short term (max.)	Average	°C	90
Vicat softening temperature	DIN EN ISO 306, Vicat B	°C	96
Electrical properties			
Surface resistivity	DIN EN 61340	Ω	> 10 ¹²
Volume resistivity	DIN EN 61340	Ω	> 10 ¹²

