

### Technical Data Sheet

## Polystone® G CubX® UV-stabilized white

PE-HD (PE 100)

#### Typical characteristics

- High longitudinal and transversal stiffness
- Good handling
- Low weight
- Good thermal insulation
- Good machinability
- Good weldability
- Chemical resistant
- UV-resistant

#### Typical industries

- Chemical Processing Industry
- Drinking & Waste Water Technology
- Chemical storage tanks
- Mechanical Engineering Industry
- Aquafarming

	Test method	Unit	Guideline value
<b>Properties for the full cross-ribbed twin-wall sheet</b>			
Thermal conductivity	ISO 8302   Tested with: GHP 500-1, Single-sheet process	W / (m * K)	Lambda 0,16
Density	DIN EN ISO 1183	g / cm <sup>3</sup>	0,3
Area weight		kg/m <sup>2</sup>	18,6
Weld strength lattice / covering sheets		MPa	≥ 16
Flatness	DIN EN ISO 15860	mm/m	4
<b>Properties for the covering sheets</b>			
Density, RT	DIN EN ISO 1183	g / cm <sup>3</sup>	0,96
Yield stress	DIN EN ISO 527	MPa	24
Elongation at break	DIN EN ISO 527	%	> 50
Tensile modulus of elasticity	DIN EN ISO 527	MPa	1000
Notched impact strength	DIN EN ISO 179	kJ / m <sup>2</sup>	20
Dielectric constant	IEC 60250		2,5
Surface resistivity	DIN EN 62631-3-2		>10 <sup>14</sup>

