

Technical Data Sheet

LURANYL[®] HT 200



PPE+PA Blend; very high heat resistance

<i>Properties</i>	<i>Unit</i>	<i>Test Method</i>	<i>Test Conditions</i>	<i>Value*</i>	<i>Remarks</i>
<i>Mechanical</i>					
Tensile Modulus	MPa	ISO 527	23°C 1mm/min	2,300	
Tensile Strength	MPa	ISO 527	23°C 50 mm/min	60	
Elongation at Break	%	ISO 527	23°C 50 mm/min	10	
Impact Strength Notched (Charpy)	kJ/m ²	ISO 179/1eA	80 x 10 x 4 mm 23°C	8	
Impact Strength (Charpy)	kJ/m ²	ISO 179/1eU	80 x 10 x 4 mm 23°C	60	
<i>Physical</i>					
Density	g/cm ³	ISO 1183	23°C, 50% RH	1.06	
Water Absorption	%	ISO 62	23°C, 24 h	< 0.35	
<i>Thermal</i>					
Vicat Softening Temperature (B 50)	°C	ISO 306	50°C/h 50N	200	
Flammability (own test)	Class	UL 94	1.6 mm	HB	

* = Average figures which could vary with each production batch due to addition of pigments, antistatic agents, slip agents, light stabilizers or other additives.

ROMIRA GMBH