

# Technical Data Sheet

## LURANYL® KR 2460/3



PPE+PS-I Blend with halogen free flame retardant; very high heat resistance

<i>Properties</i>	<i>Unit</i>	<i>Test Method</i>	<i>Test Conditions</i>	<i>Value*</i>	<i>Remarks</i>
<i>Mechanical .....</i>					
Tensile Modulus	MPa	ISO 527	23°C 1mm/min	2,500	
Tensile Strength	MPa	ISO 527	23°C 50 mm/min	65	
Elongation at Yield	%	ISO 527	23°C 50 mm/min	5	
Flexural Strength	MPa	ISO 178	23°C 2 mm/min	120	
Impact Strength Notched (Charpy)	kJ/m <sup>2</sup>	ISO 179/1eA	80 x 10 x 4 mm 23°C	18	
Impact Strength (Charpy)	kJ/m <sup>2</sup>	ISO 179/1eU	80 x 10 x 4 mm 23°C / -30°C	n.b. / n.b.	
<i>Physical .....</i>					
Density	g/cm <sup>3</sup>	ISO 1183	23°C, 50% RH	1.08	
Water Absorption	%	ISO 62	23°C, 24 h	< 0.15	
<i>Thermal .....</i>					
Heat Distortion Temperature (HDT A)	°C	ISO 75	1.80 MPa	128	
Vicat Softening Temperature (B 50)	°C	ISO 306	50°C/h 50N	160	
Melt Volume Rate MVR	cm <sup>3</sup> /10 min	ISO 1133	250°C 21.6 kg	10	
Thermal Conductivity	W/(K.m)	DIN 52612	260x260x10 mm	0.19	
Linear Thermal Expansion	10 <sup>-4</sup> · K <sup>-1</sup>	ISO 11359-2	23°C - 80°C	0.6 - 0.7	
Moulding Shrinkage	%	ISO 294-4	23°C 3,2 mm	0.5 - 0.7	
Flammability	Class	UL 94	1.6 mm	V-0	UL listed

\* = Average figures which could vary with each production batch due to addition of pigments, antistatic agents, slip agents, light stabilizers or other additives.

**ROMIRA GMBH**