



# SOUTHERN POLYMER

An **AUDIA**® Company



## PRIMALENE®

Southern Polymer

## WPP261N

A 35 melt flow medium impact copolymer

### TYPICAL APPLICATIONS:

- Automotive
- Housewares
- Packaging

### Features:

- Nucleation
- Low gloss
- High impact resistance
- FDA 21 CFR 177.1520

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16 k g)	35.0 g/10 min	D-1238
Tensile Strength, Yield	3,500 psi	D-638
Elongation, Break	>50 %	D-638
Flexural Modulus, 23 °C	190,000 psi	D-790B
Notched Izod Impact Strength, 23 °C	2.5 ft-lb/in	D-256
Rockwell Hardness	79 R	D-785
Flammability	27.5 mm/min	FMVSS 302
Shrinkage, 23 °C	0.016 in/in	D-955
Heat Deflection Temperature at 66 psi	220 °F	D-648