



SOUTHERN POLYMER

An **AUDIA**® Company



PRIMALENE®

Southern Polymer

WPP151F

An 18 melt homopolymer polypropylene

TYPICAL APPLICATIONS:

- Staple fiber
- BCF
- Filament yarn
- Geotextile and agriculture
- Injection molding

Features:

- Superior processing stability
- Anti gas-fade stabilization
- Good tear strength

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16 kg)	18.0 g/10 min	D-1238
Density (Method B)	0.902 s gr 23/23°C	D-792
Tensile Strength, Yield (2 in/min)	5,000 psi	D-638
Tensile Elongation, Yield (2 in/min)	9%	D-638