



SOUTHERN POLYMER

An **AUDIA**® Company



PRIMALENE®

Southern Polymer

WPP111

A low melt flow homopolymer polypropylene

TYPICAL APPLICATIONS:

- Strapping
- Profiles

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16kg)	1.3 g/10 min	D-1238
Flexural Modulus (0.05 in/min, 1% Secant)	185,000 psi	D-790A
Tensile Strength, Yield (2 in/min)	4,800 psi	D-638
Tensile Elongation, Yield (2 in/min)	11%	D-638
Notched Izod Impact Strength, 23 °C	0.5 ft-lbs/in	D-256A
Rockwell Hardness	101 R	D-785