



SOUTHERN POLYMER

An **AUDIA**® Company



PRIMALENE®

Southern Polymer

WPP261T

A 35 melt flow medium impact copolymer

TYPICAL APPLICATIONS:

- Injection molded caps and closures
- Housewares
- Opaque containers

Features:

- Nucleation and anti-stat
- High gloss
- Good impact resistance and stiffness
- Low warpage
- Fast cycle times
- FDA compliant

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16kg)	35.0 g/10 min	D-1238
Density	0.902 sp gr 23/23 °C	D-792
Tensile Strength, Yield (2 in/min)	4,500 psi	D-638
Elongation, Yield	7%	D-638
Flexural Modulus (0.05 in/min, 1% Secant)	215,000 psi	D-790
Notched Izod Impact Strength, 73 °F	1.0 ft-lb/in	D-256
DTUL at 66 psi – Unannealed	116 °C	D-648