



PRIMALENE®

Southern Polymer

WPP161F

A 34 melt homopolymer polypropylene

TYPICAL APPLICATIONS:

- Fine denier spunbond nonwovens
- High-speed spinning
- Continuous filament yarn

Features:

- Low smoke/condensate
- Narrow MWD

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16 kg)	34.0 g/10 min	D-1238
Tensile Strength, Yield (2 in/min)	4,700 psi	D-638
Elongation, Yield (2 in/min)	11%	D-638
Flexural Modulus (0.05 in/min, 1% Secant)	170,000 psi	D-790A
Notched Izod Impact Strength, 23 °C	0.4 ft-lb/in	D-256A
Rockwell Hardness	101 R	D-785