



## PRIMALENE®

Southern Polymer

## WPP151T

A 20 melt flow homopolymer polypropylene

### TYPICAL APPLICATIONS:

- Caps and closures
- Toys
- Housewares
- Opaque containers

### Features:

- High stiffness
- Nucleated
- Excellent anti-static properties
- Fast cycle times

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16 kg)	20.0 g/10 min	D-1238
Density (Method B)	0.902 sp gr 23/23 °C	D-792
Flexural Modulus, 1% Secant (0.05 in/min)	250,000 psi	D-790
Tensile Elongation, Yield (2 in/min)	7.5%	D-638
Tensile Strength, Yield (2 in/min)	5,500 psi	D-638
Notched Izod Impact Strength, 73 °F	0.6 ft-lb/in	D-256
Rockwell Hardness	90 R	D-785