



## PRIMALENE®

Southern Polymer

## WPP351

A 25 melt flow high impact copolymer polypropylene

### TYPICAL APPLICATIONS:

- Toys
- Housewares
- Compounding

### Features:

- High gloss
- Low temperature impact resistance
- Good processability
- Good stiffness

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16 kg)	25.0 g/10 min	D-1238
Density	0.902 sp gr 23/23 °C	D-792
Elongation, Yield	6.6%	D-638
Tensile Strength, Yield (2 in/min)	3,300 psi	D-638
Flexural Modulus (0.05 in/min, 1% Secant)	150,000 psi	D-790
Heat Deflection Temperature at 66 psi	140 °F	D-648
Notched Izod Impact Strength, 73 °F	No Break	D-256
Gardner Gloss (60°)	86	D-523