



PRIMALENE®

Southern Polymer

WPP461C

A 35 melt flow random clarified copolymer polypropylene

TYPICAL APPLICATIONS:

- Housewares
- Packaging
- Containers

Features:

- Good processing characteristics
- See-through clarity
- Contact clarity

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16 kg)	35.0 g/10 min	D-1238
Density	0.902 sp gr 23/23 °C	D-792
Tensile Strength, Yield (2 in/min)	4,100 psi	D-638
Tensile Elongation, Yield	12%	D-638
Flexural Modulus, (0.05 in/min, 1% Secant)	160,000 psi	D-790
Notched Izod Impact Strength, 73 °F	1.0 ft-lbs/in	D-256
DTUL at 66 psi – Unannealed	82 °C	D-648
Haze	10%	D-1003