



SOUTHERN POLYMER

An **AUDIA**® Company



PRIMALENE®

Southern Polymer

WPP391

A fractional melt flow high impact copolymer polypropylene

TYPICAL APPLICATIONS:

- Extrusion processes

Physical Properties	Typical Values*	Test Method(s)
Melt Flow Rate (230 °C/2.16kg)	0.5 g/10 min	D-1238
Density	0.902 sp gr	D-792
Tensile Strength, Yield (2 in/min)	3,400 psi	D-638
Tensile Elongation, Yield	13.0%	D-638
Flexural Modulus (0.05 in/min, 1% Secant)	175,000 psi	D-790
Notched Izod Impact, 73 °F	No Break	D-256
DTUL at 66 psi - Unannealed	80 °C	D-648