



PRIMALENE®

Southern Polymer

WPP694M

A metallocene linear low density polyethylene

TYPICAL APPLICATIONS:

- Overwrap
- Bakery
- Stand-up pouches

Features:

- High clarity
- Excellent gloss
- Good toughness and stiffness
- Processing aid
- Slip: zero
- Anti-block: zero

Physical Properties	Typical Values*	Test Method(s)
Melt Index (190 °C/2.16 kg)	0.9 g/10 min	D-1238
Density	0.933 g/cm ³	D-1505
Film Properties at 1 mil	Typical Values*	Test Method(s)
Haze	5%	D-1003
Gloss, 60°	123	D-2457
COF	0.7	D-1894
Dart	80 g/mil	D-1709
Elmendorf Tear, MD. TD	35 g/mil 300 g/mil	D-1922
Tensile Strength, Break MD. TD	2,590 psi 3,220 psi	D-882
Tensile Modulus, 1% Secant MD TD	7,680 psi 6,650 psi	D-882
Elongation, Break MD TD	62,600 psi 84,900 psi	D-882