



PRIMALENE®

Southern Polymer

WPP692M

A metallocene linear low density polyethylene

TYPICAL APPLICATIONS:

- Seal layer in co-extrusions
- Heavy duty packaging
- Clarity packaging

Features:

- High clarity
- Excellent gloss
- Excellent toughness
- Good sealability
- Processing aid
- Slip: zero
- Anti-block: zero

Physical Properties	Typical Values*	Test Method(s)
Melt Index (190 °C/2.16 kg)	1.0 g/10 min	D-1238
Density	0.918 g/cm ³	D-1505
Film Properties at 1 mil	Typical Values*	Test Method(s)
Haze	4%	D-1003
Gloss, 60°	130	D-2457
COF	>1	D-1894
Dart	800 g/mil	D-1709
Elmendorf Tear, MD. TD	230 g/mil 500 g/mil	D-1922
Tensile Strength, Yield, MD. TD	1,550 psi 1,380 psi	D-882
Tensile Strength, Break MD. TD	8,500 psi 7,500 psi	D-882



SOUTHERN POLYMER

An **AUDIA**® Company



Tensile Modulus, 1% Secant MD	25,400 psi	D-882
TD	27,700 psi	
Elongation, Break MD	450%	D-882
TD	600%	
