



## PRIMALENE®

Southern Polymer

## WPP692QD

A hexane linear low density polyethylene

### TYPICAL APPLICATIONS:

- Industrial liners
- Garment and carrier bags
- General purpose packaging

### Features:

- Good stiffness at thin gauges
- Good drawdown
- Excellent processing characteristics
- Slip: high
- Anti-block: high

Physical Properties	Typical Values*	Test Method(s)
Melt Index	0.9 g/10 min	D-1238
Density	0.918 g/cm <sup>3</sup>	D-1505
Film Properties at 1 mil	Typical Values*	Test Method(s)
Haze	21%	D-1003
Gloss, 60°	70	D-2457
COF	0.15	D-1894
Dart	325 g/mil	D-1709
Elmendorf Tear, MD. TD	400 g/mil 650 g/mil	D-1922
Tensile Strength, Break MD. TD	4,300 psi 2,900 psi	D-882
Tensile Modulus, 1% Secant MD TD	30,000 psi 33,000 psi	D-882
Elongation, Break MD TD	400% 600%	D-882