



SOUTHERN POLYMER

An AUDIA® Company



PRIMALENE®

Southern Polymer

WPP733P

A film grade high density polyethylene

TYPICAL APPLICATIONS:

- Moisture sensitive packaging
- Food packaging
- Blends
- Co-extrusions
- Release liners

Features:

- Excellent MVTR
- Improved stiffness properties
- Improved scuff resistance
- Good processability
- Low gel levels
- FDA 21 CFR 177.1520 (c) 3.2a

Physical Properties	Typical Values*	Test Method(s)
Melt Index (Condition 190 °C/2.16 kg)	8.0 g/10 min	D-1238
Density	0.962 g/cm ³	D-1505
Vicat Softening Temperature	250 °F	D-1525