



PRIMALENE®

Southern Polymer

WPP541K

An extrusion coating grade low density polyethylene

TYPICAL APPLICATIONS:

- Laminations
- Food packaging
- General paper and board coating
- General flexible packaging

Features:

- Excellent processability
- Hi-line speed
- Low neck-in
- Good drawdown characteristics
- High temperature extrusion stability

Physical Properties	Typical Values*	Test Method(s)
Melt Index (190 °C/2.16 kg)	13.0 g/10 min	D-1238
Density	0.917 g/cm ³	D-1505
Vicat Softening Temperature	189 °F	D-1525
Melting Point	216 °F	D-3418
WVTR	1.52 g/100in ² /day	F-1249
OTR	490 cm ³ /100in ² /day	D-3985