

UPM FORMI EFP 30

PP Spritzgießtype mit 30% Zellulosefasern.

	Properties	Test condition	Method	Unit	Value
Impact	Charpy Notched Impact Strength		ISO 179/1eA	kJ/m ²	5,3
	Charpy Unnotched Impact Strength		ISO 179/1eU	kJ/m ²	32
Physical	Density		ISO 1183	g/cm ³	1,02
Mechanical	Tensile Strength		ISO 527-2	N/mm ²	43
	Tensile Modulus		ISO 527-2	N/mm ²	3000
	Tensile Strain		ISO 527-2	%	4,9