

UPM FORMI SP 30

PP Spritzgießtype mit 30% Zellulosefasern.

	Properties	Test condition	Method	Unit	Value
Impact	Charpy Notched Impact Strength		ISO 179/1eA	kJ/m ²	5,5
	Charpy Unnotched Impact Strength		ISO 179/1eU	kJ/m ²	33
Physical	Density		ISO 1183	g/cm ³	1,02
Mechanical	Tensile Strength		ISO 527-2	N/mm ²	47
	Tensile Modulus		ISO 527-2	N/mm ²	2900
	Tensile Strain		ISO 527-2	%	5,1