

# UPM FORMI GP 30

PP Spritzgießtype mit 30% Zellulosefasern.

	Properties	Test condition	Method	Unit	Value
Impact	Charpy Notched Impact Strength		ISO 179/1eA	kJ/m <sup>2</sup>	4,2
	Charpy Unnotched Impact Strength		ISO 179/1eU	kJ/m <sup>2</sup>	34
Physical	Density		ISO 1183	g/cm <sup>3</sup>	1,02
Mechanical	Tensile Strength		ISO 527-2	N/mm <sup>2</sup>	41
	Tensile Modulus		ISO 527-2	N/mm <sup>2</sup>	2900
	Tensile Strain		ISO 527-2	%	4,8