

# UPM FORMI GP 50

PP Spritzgießtype mit 50% Zellulosefasern.

	Properties	Test condition	Method	Unit	Value
Impact	Charpy Notched Impact Strength		ISO 179/1eA	kJ/m <sup>2</sup>	3,7
	Charpy Unnotched Impact Strength		ISO 179/1eU	kJ/m <sup>2</sup>	29
Physical	Density		ISO 1183	g/cm <sup>3</sup>	1,12
Mechanical	Tensile Strength		ISO 527-2	N/mm <sup>2</sup>	58
	Tensile Modulus		ISO 527-2	N/mm <sup>2</sup>	4700
	Tensile Strain		ISO 527-2	%	3