

# Kepital F25-03HT

A medium-low viscosity grade for general injection molding with high stiffness, high toughness and a good friction & wear resistance.

	Properties	Test condition	Method	Unit	Value
Physical	Density		ISO 1183	g/cm <sup>3</sup>	1,41
	Melt Flow Rate		ISO 1133	g/10min	13
	Molding Shrinkage (Flow Direction)	t 3mm, Ø 100mm	KEP Method	%	2
	Thermal	Heat Deflection Temperature (HDT)	1.8 MPa	ISO 75-1,2	°C
Flammability			UL94	Class	HB
Mechanical	Tensile Strength	23°C	ISO 527-1,2	MPa	64
	Flexural Strength	23°C	ISO 178	MPa	90
	Flexural Modulus	23°C	ISO 178	MPa	2.600
	Charpy Notched Impact Strength		ISO 179/1eA	kJ/m <sup>2</sup>	6
	Nominal Strain at Break	23°C	ISO 527-1,2	%	27
Electrical	Surface Resistivity		IEC 60093	□	1 x 10 <sup>16</sup>
	Volume Resistivity		IEC 60093	□ □ cm	1 x 10 <sup>14</sup>
	Dielectric Strength		IEC 60243-1	kV /mm	19