

# KEPITAL GD-52

**An easy flowing grade for general injection molding and so suitable for parts requiring a good weather resistance and low gloss**

	Properties	Test condition	Method	Unit	Value
Physical	Density		ISO 1183	g/cm <sup>3</sup>	1,41
	Melt Flow Rate		ISO 1133	g/10min	25
Thermal	Flammability		UL94	Class	HB
Mechanical	Tensile Strength	23°C	ISO 527-1,2	MPa	59
	Flexural Strength	23°C	ISO 178	MPa	86
	Flexural Modulus	23°C	ISO 178	MPa	2.750
	Charpy Notched Impact Strength		ISO 179/1eA	kJ/m <sup>2</sup>	4
	Nominal Strain at Break	23°C	ISO 527-1,2	%	14
Electrical	Surface Resistivity		IEC 60093	Ω	1 x 10 <sup>16</sup>
	Volume Resistivity		IEC 60093	Ω • cm	1 x 10 <sup>14</sup>
	Dielectric Strength		IEC 60243-1	kV /mm	19