

KEPITAL GR-30

A low viscosity grade for general injection molding. Suitable for use where wear resistance, low noise and excellent dimensional stability are required when contacting metal and resin.

	Properties	Test condition	Method	Unit	Value
Physical	Density		ISO 1183	g/cm ³	1,43
	Melt Flow Rate		ISO 1133	g/10min	20
	Molding Shrinkage (Flow Direction)	t 3mm, Ø 100mm	KEP Method	%	1,8
Thermal	Flammability		UL94	Class	HB
Mechanical	Tensile Strength	23°C	ISO 527-1,2	MPa	48
	Flexural Strength	23°C	ISO 178	MPa	66
	Flexural Modulus	23°C	ISO 178	MPa	2150
	Charpy Notched Impact Strength		ISO 179/1eA	kJ/m ²	5,5
	Nominal Strain at Break	23°C	ISO 527-1,2	%	40
Electrical	Surface Resistivity		IEC 60093	Ω	1 • 10 ¹⁶
	Volume Resistivity		IEC 60093	Ω • cm	1 • 10 ¹⁴