

Kepital F20-52U

A medium viscosity UV-stabilized grade suitable for out-door use (colored)

Especially for the products which it needs impact resistance.

	Properties	Test condition	Method	Unit	Value
Physical	Density		ISO 1183	g/cm ³	1,38
	Melt Flow Rate		ISO 1133	g/10min	8,5
Thermal	Flammability		UL94	Class	HB
Mechanical	Tensile Strength	23°C	ISO 527-1,2	MPa	45
	Flexural Strength	23°C	ISO 178	MPa	55
	Flexural Modulus	23°C	ISO 178	MPa	1.700
	Charpy Notched Impact Strength		ISO 179/1eA	kJ/m ²	10
	Nominal Strain at Break	23°C	ISO 527-1,2	%	110
Electrical	Surface Resistivity		IEC 60093	Ω	1 × 10 ¹⁴
	Volume Resistivity		IEC 60093	Ω cm	1 × 10 ¹²