

KEPITAL TE-21

Talcum reinforced and low viscosity grade for general injection molding. It's suitable for parts requiring more reducing deformation than that of standard grade under the same stress. Exhibits excellent dimensional accuracy.

	Properties	Test condition	Method	Unit	Value
Physical	Density		ISO 1183	g/cm ³	1,39
	Melt Flow Rate		ISO 1133	g/10min	11
	Molding Shrinkage (Flow Direction)	t 3mm, Ø 100mm	KEP Method	%	1,9
Thermal	Heat Deflection Temperature (HDT)	1.8 MPa	ISO 75-1,2	°C	84
	Flammability		UL94	Class	HB
Mechanical	Tensile Strength	23°C	ISO 527-1,2	MPa	57
	Flexural Strength	23°C	ISO 178	MPa	76
	Flexural Modulus	23°C	ISO 178	MPa	2.150
	Charpy Notched Impact Strength		ISO 179/1eA	kJ/m ²	8
	Nominal Strain at Break	23°C	ISO 527-1,2	%	40
Electrical	Surface Resistivity		IEC 60093	Ω	1x 10 ¹⁶
	Volume Resistivity		IEC 60093	Ω • cm	1x 10 ¹⁴