

INFINO WP-1100

	Properties	Test condition	Method	Unit	Value
Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,22
	Melt Flow Index	250°C, 2,16kg	ISO 1133	g/10min	40
	Mold Shrinkage	-	ISO 2577	%	0,3~0,5
Thermal	Heat Deflection Temperature	18,56kgf/cm ²	ISO 75-2	°C	119
Mechanical	Charpy Impact Strength (notched)	4mm	ISO 179 1eA	KJ/m ²	12
	Stress at Yield	50mm/min	ISO 527	Kg/cm ²	92
	Flexural Strength	2mm/min	ISO 178	Kgf/cm ²	150
	Flexural Modulus	2mm/min	ISO 178	Kgf/cm ²	4,7