

Niblend S85

PC-ABS alloy of very high termic resistance, suitable to meet the ball pressure test at 125 °C

	Properties	Test condition	Method	Unit	Value
Rheological	Melt Flow Index	260°C / 5 kg	ASTM D1238	g/10min	18
Mechanical	Tensile Stress at Yield	50 mm/min.	ASTM D638	MPa	55
	Flexural Maximum Stress	1,3 mm/min	ASTM D790	MPa	75
	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	2300
	Izod Notched Impact Strength	23°C/3mm	ASTM D256	J/m	500
	Izod Notched Impact Strength	-20°C/3mm	ASTM D256	J/m	150
	Rockwell Hardness	23°C	ASTM D785	M-scale	118
	Elongation	50 mm/min	ASTM D638	%	30
Thermal	Vicat Softening Temperature	49N / 120°C/h	ASTM D 1525	°C	138
	Heat Distortion Temperature H.D.T	1.82 MPa	ASTM D648	°C	127
	Linear Expansion Coefficient	23°C/55°C	ISO 11359-2	10 ⁻⁵ K ⁻¹	7
Flame Behaviour	Glow Wire Temperature (G.W.T)	S=2.0 mm	IEC 695-2-1	°C	650
	UL 94 Rating	S=1.6 mm	UL 94	class	HB
	UL 94 Rating	S=3.2 mm	UL 94	class	HB
Electrical	Relative Permittivity	1 Mhz – dry	IEC 60250	-	2,9
	Dissipation Factor	1 Mhz – dry	IEC 60250	-	0,05
	Dielectric Strength	S=1 mm	IEC 60243-1	KV/mm	25
	Surface Resistivity	dry	IEC 60093	□	10 ¹⁵
	Volume Resistivity	dry	IEC 60093	□ □ cm	10 ¹⁵
Various	Density		ASTM D792	g/cm ³	1,17
	Humidity Content at Equilibrium	23°C / 50 % U.R.	ISO 62	%	0,2



	Properties	Test condition	Method	Unit	Value
	Moulding Shrinkage	parallel	-	%	0,4 – 0,8

TEKUMA KUNSTSTOFF GMBH