

# Niretan A F35

Polyamide 66, reinforced with 35 % of glass fibre, for injection moulding of parts that needs high rigidity and dimensional stability, also after conditioning.

## &nbsp;

|                 | Properties                        | Test condition | Method      | Unit                             | Value                              |
|-----------------|-----------------------------------|----------------|-------------|----------------------------------|------------------------------------|
| Mechanical      | Tensile Stress at Break           | 5 mm/min       | ASTM D638   | MPa                              | 180/120                            |
|                 | Flexural Maximum Stress           | 1,3 mm/min     | ASTM D790   | MPa                              | 270/180                            |
|                 | Flexural Elastic Modulus          | 1,3 mm/min     | ASTM D790   | MPa                              | 10000/7000                         |
|                 | Izod Notched Impact Strength      | 23°C/3mm       | ASTM D256   | J/m                              | 90/130                             |
|                 | Izod Notched Impact Strength      | -20°C/3mm      | ASTM D256   | J/m                              | 70/100                             |
|                 | Rockwell Hardness                 | 23°C           | ASTM D785   | R-scale                          | 118/90                             |
|                 | Elongation                        | 50 mm/min      | ASTM D638   | %                                | 2,0/3,5                            |
| Thermal         | Heat Distortion Temperature H.D.T | 1.82 MPa       | ASTM D648   | °C                               | 250                                |
|                 | Linear Expansion Coefficient      | 23°C/55°C      | ISO 11359-2 | 10 <sup>-5</sup> K <sup>-1</sup> | 3                                  |
| Flame Behaviour | Glow Wire Temperature (G.W.T)     | S=2.0 mm       | IEC 695-2-1 | °C                               | 650                                |
|                 | UL 94 Rating                      | S=1.6 mm       | UL 94       | class                            | HB                                 |
|                 | UL 94 Rating                      | S=3.2 mm       | UL 94       | class                            | HB                                 |
| Electrical      | Relative Permittivity             | 1 Mhz - dry    | IEC 60250   | -                                | 3,5/4,0                            |
|                 | Dissipation Factor                | 1 Mhz - dry    | IEC 60250   | -                                | 0,02/0,1                           |
|                 | Dielectric Strength               | S=1 mm         | IEC 60243-1 | KV/mm                            | 30/35                              |
|                 | Surface Resistivity               | dry            | IEC 60093   | □                                | 10 <sup>14</sup> /10 <sup>13</sup> |
|                 | Volume Resistivity                | dry            | IEC 60093   | □ □ cm                           | 10 <sup>15</sup> /10 <sup>12</sup> |
| Various         | Moulding Shrinkage                | parallel       | -           | %                                | 0,2-0,6                            |
| Physical        | Density                           | 23°C           | ASTM D792   | g/cm <sup>3</sup>                | 1,41                               |
|                 | Water Absorption                  | 24h - 23°C     | ASTM D570   | %                                | 6                                  |



| Properties                      | Test condition | Method | Unit | Value |
|---------------------------------|----------------|--------|------|-------|
|                                 |                |        |      | 2,2   |
| Cristalline Melting Temperature | DSC            | -      | °C   | 260   |