

Niretan B SV15

	Properties	Test condition	Method	Unit	Value
Mechanical	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	3000
	Izod Notched Impact Strength	23°C/3mm	ASTM D256	J/m	90
Thermal	Vicat Softening Temperature	49N / 120°C/h	ASTM D 1525	°C	195
Physical	Density	23°C	ASTM D792	g/cm ³	1,22