

STAREX NH-0926

ABS halogenfrei, flammgeschützt

	Properties	Test condition	Method	Unit	Value
Flammability	Flammability	V-2	UL94	mm	0,75,3,0
Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,05
	Melt Flow Index	200°C, 5kg	ISO 1133	g/10min	3,5
Thermal	Vicat Softening Temperature	5kg, 50°C/hr	ISO R 306	°C	98
Mechanical	Rockwell Hardness	R-scale	ISO 2039-2	-	108
	Tensile Strength	50mm/min	ISO 527	MPa	44
	Flexural Strength	2,8mm/min	ISO 178	MPa	63
	Flexural Modulus	2,8mm/min	ISO 178	MPa	2296
	Izod Impact Strength (notched)	4mm	ISO 180 1A	KJ/m ²	17