

STAREX SR-7300

Material with superior chemical resistance that can be applied to the interior/exterior material of house hold appliances that require he at resistance

	Properties	Test condition	Method	Unit	Value
Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,1
	Melt Flow Index	250°C,10kg	ISO 1133	g/10min	16
Thermal	Heat Deflection Temperature (unannealed)	1.8 MPa, 4.0mm	ISO 75-2	°C	78
	Heat Deflection Temperature (unannealed)	0.45 MPa, 4.0mm	ISO 75-2	°C	94
	Heat Deflection Temperature (annealing)	1.8 MPa, 4.0mm	ISO 75-2	°C	92
	Heat Deflection Temperature (annealing)	0.45 MPa, 4.0mm	ISO 75-2	°C	101
	Vicat Softening Temperature	B/50	ISO R 306	°C	104
Mechanical	Tensile Strength at Yield	50mm/min	ISO 527	MPa	44
	Tensile Strain at Break	50mm/min	ISO 527	%	19
	Tensile Modulus	50mm/min	ISO 527	MPa	2000
	Tensile Strength at Break	50mm/min	ISO 527	MPa	30
	Flexural Strength	2mm/min	ISO 178	MPa	65
	Flexural Modulus	2mm/min	ISO 178	MPa	2100
	Izod Impact Strength (notched)	at 23°C, 4mm	ISO 180 1A	KJ/m ²	34
	Charpy Impact Strength (V-notched)	23°C, 4mm	ISO 179 1eA	KJ/m ²	28
	Rockwell Hardness	R-scale	ISO 2039-2	-	106