

TECHNICAL DATA SHEET

Greenflex® FF 35

Versalis S.p.A

EVAC

Processing

Blown film extrusion, Profile extrusion

Delivery Form

Pellets

Features

Copolymer

Applications

Packaging

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	0.7	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Mechanical Properties	Value	Unit	Standard
Shore D hardness	42		ISO 7619-1
Shore A hardness, 15s	94		ISO 7619-1
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	102	°C	ISO 11357-1/-3
Coeff. of linear therm. expansion, parallel	27	E-6/K	ISO 11359-1/-2
Optical Properties	Value	Unit	Standard
Gloss, 45°	75		ISO 2813
Haze	3		ISO 14782
Film Properties	Value	Unit	Standard
Stress at yield, parallel	7	MPa	ISO 527-3
Stress at yield, normal	6	MPa	ISO 527-3
Stress at break, normal	28	MPa	ISO 527-3
Maximum strain, parallel	480	%	ISO 527-3
Maximum strain, normal	650	%	ISO 527-3
Dynamic coefficient of friction	0.5		ISO 8295
Type of extrusion	blown		
Thickness of specimen	0.07	mm	