

TECHNICAL DATA SHEET

Greenflex® MP 34

Versalis S.p.A
EVAC

Processing

Injection molding

Pellets

Features

Foamable, Copolymer

Delivery Form

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	9	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	

Mechanical Properties	Value	Unit	Standard
Yield stress	7	MPa	ISO 527
Flexural modulus, 23°C	90	MPa	ISO 178
Shore D hardness	40		ISO 7619-1
Shore A hardness, 15s	95		ISO 7619-1

Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	95	°C	ISO 11357-1/-3