

TECHNICAL DATA SHEET

PHARMALENE® FL 65 PH BA

Versalis S.p.A
EVAC

Processing

Blown film extrusion, Film extrusion, Other extrusion

Delivery Form

Pellets

Features

Heat sealable, Copolymer

Certifications

Contains renewable resources, Food contact, Food approval 10/2011, Food approval FDA 21 CFR, Medical grade, US Pharmacopeia class VI approved

Applications

Medical, Packaging

Product Text

Product Information

Pharmalene FL 65 PH BA will be bio attributed for 72%.

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	2.5	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Mechanical Properties	Value	Unit	Standard
Flexural modulus, 23°C	10	MPa	ISO 178
Shore D hardness	32		ISO 7619-1
Shore A hardness, 15s	75		ISO 7619-1
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	74	°C	ISO 11357-1/-3
Vicat softening temperature, A	44	°C	ISO 306
Optical Properties	Value	Unit	Standard
Haze	1		ISO 14782
Gloss	90		ASTM D 2457
Other Properties	Value	Unit	Standard
Density	952	kg/m ³	ISO 1183

PHARMALENE® FL 65 PH BA

Versalis S.p.A

Film Properties	Value	Unit	Standard
Stress at yield, parallel	4	MPa	ISO 527-3
Stress at yield, normal	3.5	MPa	ISO 527-3
Stress at break, parallel	31	MPa	ISO 527-3
Stress at break, normal	28	MPa	ISO 527-3
Maximum strain, parallel	600	%	ISO 527-3
Maximum strain, normal	800	%	ISO 527-3
Dart drop A	500	g	ISO 7765-1
Dynamic coefficient of friction	0.5		ISO 8295
Type of extrusion	blown		

Processing Recommendation Extrusion	Value	Unit	Standard
Type of extrusion	blown		
Melt temperature	150 - 170	°C	