

TECHNICAL DATA SHEET

PHARMALENE® FL 35 PH BA

Versalis S.p.A

EVAC

Processing

 Injection molding, Blown film extrusion, Film extrusion,
 Other extrusion

Delivery Form

Pellets

Features

Heat sealable, Copolymer

Certifications

 Contains renewable resources, Food contact, Food approval
 10/2011, Food approval FDA 21 CFR, Medical grade, US
 Pharmacopeia class VI approved

Applications

Medical

Product Text

Product Information

Pharmalene FL 35 PH BA will be bio attributed for 91%.

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	2.5	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Mechanical Properties	Value	Unit	Standard
Flexural modulus, 23°C	90	MPa	ISO 178
Shore D hardness	42		ISO 7619-1
Shore A hardness, 15s	94		ISO 7619-1
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	97	°C	ISO 11357-1/-3
Vicat softening temperature, A	72	°C	ISO 306
Optical Properties	Value	Unit	Standard
Haze	3		ISO 14782
Gloss	80		ASTM D 2457
Other Properties	Value	Unit	Standard
Density	929	kg/m³	ISO 1183

PHARMALENE® FL 35 PH BA

Versalis S.p.A

Film Properties	Value	Unit	Standard
Stress at yield, parallel	6	MPa	ISO 527-3
Stress at yield, normal	6	MPa	ISO 527-3
Stress at break, parallel	28	MPa	ISO 527-3
Stress at break, normal	28	MPa	ISO 527-3
Maximum strain, parallel	500	%	ISO 527-3
Maximum strain, normal	700	%	ISO 527-3
Dart drop A	450	g	ISO 7765-1
Dynamic coefficient of friction	0.5		ISO 8295
Type of extrusion	blown		
Processing Recommendation Extrusion	Value	Unit	Standard
Type of extrusion	blown		
Melt temperature	170 - 200	°C	