

TECHNICAL DATA SHEET

LUMICENE® mPE M 3410 EP

TotalEnergies

Processing

Blown film extrusion, Film extrusion

Special Characteristics

Transparent

Features

Blending resin, High gloss

Chemical Resistance

Oxidation resistance

Certifications

Food contact

Applications

Packaging

Product Text

Product Information

Lumicene mPE M 3410 EP is a metallocene based Medium Density Polyethylene with hexene as comonomer.

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	0.9	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	124	°C	ISO 11357-1/-3
Optical Properties	Value	Unit	Standard
Haze	9		ISO 14782
Gloss	60		ASTM D 2457
Other Properties	Value	Unit	Standard
Density	934	kg/m ³	ISO 1183
Film Properties	Value	Unit	Standard
Stress at yield, parallel	17	MPa	ISO 527-3
Stress at yield, normal	18	MPa	ISO 527-3
Stress at break, parallel	47	MPa	ISO 527-3
Stress at break, normal	43	MPa	ISO 527-3
Maximum strain, parallel	630	%	ISO 527-3

LUMICENE® mPE M 3410 EP

TotalEnergies

Film Properties	Value	Unit	Standard
Maximum strain, normal	700	%	ISO 527-3
Dart drop A	100	g	ISO 7765-1
Type of extrusion	blown		
Thickness of specimen	0.04	mm	

Processing Recommendation Extrusion	Value	Unit	Standard
Type of extrusion	blown		
Melt temperature	180 - 230	°C	