

TECHNICAL DATA SHEET

Flexirene® FG 23 F

Versalis S.p.A
(PE-LLD)

Processing

Blown film extrusion

Delivery Form

Pellets

Additives

Antiblocking agent

Features

Blending resin, Copolymer, Butene copolymer

Chemical Resistance

Oxidation resistance

Applications

General purpose

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	1	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	121	°C	ISO 11357-1/-3
Coeff. of linear therm. expansion, parallel	45	E-6/K	ISO 11359-1/-2
Optical Properties	Value	Unit	Standard
Gloss, 45°	57		ISO 2813
Haze	11		ISO 14782
Other Properties	Value	Unit	Standard
Density	919	kg/m ³	ISO 1183
Film Properties	Value	Unit	Standard
Stress at yield, parallel	11	MPa	ISO 527-3
Stress at yield, normal	11	MPa	ISO 527-3
Stress at break, normal	35	MPa	ISO 527-3
Maximum strain, parallel	550	%	ISO 527-3
Maximum strain, normal	800	%	ISO 527-3
Dynamic coefficient of friction	0.14		ISO 8295
Type of extrusion	blown		

Flexirene® FG 23 F

Versalis S.p.A

Film Properties	Value	Unit	Standard
Thickness of specimen	0.025	mm	