

Technisches Datenblatt Technical Datasheet

Article Nr.: 26266

terXene eco HDPE BM - 2903

Material	Anwendung application	Farbe colour
Regranulat, HDPE	Blasformen Rohre, Profile	schwarz
Regranulate, HDPE	blow moulding pipes, profiles	black



Eigenschaft Property	Prüfnorm test standard	Wert value	Einheit unit
Schmelzindex Melt Index	MFI 190/2,16 (!) EN ISO 1133	0,2 - 0,5	g/10min
Dichte Density	EN ISO 1183-1	,0945 - 0,955	g/cm ³
Aschegehalt Ash content	ISO 3451-1/A/600°C	< 10	%
Feuchte Moisture	Hausnorm / internal method	0	%

#REF!			
-------	--	--	--

#REF!			
-------	--	--	--

Ursprung / Origin **EU**

zertifiziertes Recycling:

certified recycling:

nein / no



100% PIR

Nicht geeignet zur Herstellung direkter Lebensmittelverpackungen.
Trocken und vor Umwelteinflüssen geschützt lagern.

Not suited for direct food packaging.
Store under dry conditions and protected from environmental influences