

TECHNICAL DATA SHEET

# Riblene® FF 33

Versalis S.p.A  
(PE-LD)

**Processing**

Blown film extrusion

**Delivery Form**

Pellets

**Features**

Blending resin, Melt strength

**Applications**

Packaging

Processing/Physical Characteristics	Value	Unit	Standard
Melt flow index, MFI	0.8	g/10min	ISO 1133
Temperature	190	°C	
Load	2.16	kg	
Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	114	°C	ISO 11357-1/-3
Coeff. of linear therm. expansion, parallel	22	E-6/K	ISO 11359-1/-2
Optical Properties	Value	Unit	Standard
Gloss, 45°	65		ISO 2813
Haze	7.5		ISO 14782
Other Properties	Value	Unit	Standard
Density	924	kg/m <sup>3</sup>	ISO 1183
Film Properties	Value	Unit	Standard
Stress at yield, parallel	10	MPa	ISO 527-3
Stress at yield, normal	11	MPa	ISO 527-3
Stress at break, normal	19	MPa	ISO 527-3
Maximum strain, parallel	400	%	ISO 527-3
Maximum strain, normal	600	%	ISO 527-3
Dynamic coefficient of friction	0.11		ISO 8295
Type of extrusion	blown		
Thickness of specimen	0.07	mm	