

TECHNICAL DATA SHEET

Akulon® K223-HM6

Envalior
PA6-MD30

Processing

Injection molding

Delivery Form

Pellets

Additives

Release agent

Special Characteristics

Heat stabilized or stable to heat

Product Text

Product Information

30% Mineral Reinforced, Heat Stabilized

ISO 1043 PA6-MD30

Processing/Physical Characteristics	Value	Unit	Standard
Molding shrinkage, parallel	0.79	%	ISO 294-4, 2577
Molding shrinkage, normal	0.69	%	ISO 294-4, 2577
Density of melt	1156	kg/m ³	
Thermal conductivity of melt	0.32	W/(m K)	
Spec. heat capacity of melt	2450	J/(kg K)	
Eff. thermal diffusivity	1.14E-7	m ² /s	

Mechanical Properties	Value	Unit	Standard
Tensile modulus	6100	MPa	ISO 527
Stress at break	75	MPa	ISO 527
Strain at break	3.5	%	ISO 527
Poisson's ratio	0.35		ISO 527
Charpy impact strength, +23°C	40	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	40	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	3	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	2	kJ/m ²	ISO 179/1eA

Akulon® K223-HM6

Envalior


Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	135	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	205	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	40	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	40	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	
Yellow card available	yes		
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3	mm	
Yellow card available	yes		
Electrical Properties	Value	Unit	Standard
Relative permittivity, 100Hz	3.2		IEC 62631-2-1
Relative permittivity, 1MHz	3		IEC 62631-2-1
Dissipation factor, 100Hz	50	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	130	E-4	IEC 62631-2-1
Volume resistivity	1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Electric strength	30	kV/mm	IEC 60243-1
Comparative tracking index	500		IEC 60112
Other Properties	Value	Unit	Standard
Water absorption	6.6	%	Sim. to ISO 62
Humidity absorption	1.9	%	Sim. to ISO 62
Density	1380	kg/m ³	ISO 1183

Diagrams


Akulon® K223-HM6

Envalior


Stress-strain




Stress-strain



True stress-true strain




True stress-true strain




Akulon® K223-HM6

Envalior


Secant modulus-strain




Secant modulus-strain



Viscosity-shear rate




Shearstress-shear rate




Akulon® K223-HM6

Envalior


Spec. volume-Temperature (pVT)




Dynamic shear modulus-temperature



Stress-strain (isochronous) 23°C



Stress-strain (isochronous) 23°C



Processing Information

Injection molding

Injection Molding Recommendations

Steel recommendations for molds screws and barrels

Trouble shooting guideline for injection molding