



<b>TEREZ PA/ABS Blend 2000</b>			
<b>(PA6+ABS)</b>		Ter Plastics	
<b>Product Texts</b>			
High impact resistance blend with reduced moisture absorption. For injection moulding and extrusion applications.			
<b>Rheological properties</b>			
	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Melt flow index, MFI	12	g/10min	ISO 1133
MFI temperature	260	°C	ISO 1133
MFI load	5	kg	ISO 1133
<b>Mechanical properties</b>			
	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Tensile Modulus	1900	MPa	ISO 527-1/-2
Tensile Strength	40	MPa	ISO 527-1/-2
Strain at break	100	%	ISO 527-1/-2
Charpy impact strength (+23°C)	N	kJ/m <sup>2</sup>	ISO 179/1eU
Charpy notched impact strength (+23°C)	85	kJ/m <sup>2</sup>	ISO 179/1eA
Charpy notched impact strength, -30°C	25	kJ/m <sup>2</sup>	ISO 179/1eA
<b>Thermal properties</b>			
	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Temp. of deflection under load (1.80 MPa)	65	°C	ISO 75-1/-2
Temp. of deflection under load (0.45 MPa)	165	°C	ISO 75-1/-2
Vicat softening temperature, 50°C/h 50N	140	°C	ISO 306
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.6	mm	IEC 60695-11-10
<b>Other properties</b>			
	<b>Value</b>	<b>Unit</b>	<b>Test Standard</b>
<b>ISO Data</b>			
Water absorption	4.5	%	Sim. to ISO 62
Humidity absorption	1.3	%	Sim. to ISO 62
Density	1070	kg/m <sup>3</sup>	ISO 1183