


Technyl® C 216

PA6

Solvay Engineering Plastics

Product Texts

Polyamide 6, unreinforced medium viscosity, for injection moulding, short cycle time

Mechanical properties

dry / cond

Unit

Test Standard

ISO Data

| | | | |
|--|-------------|-------------------|--------------|
| Tensile Modulus | 2950 / 1100 | MPa | ISO 527-1/-2 |
| Charpy impact strength (+23°C) | N / - | kJ/m ² | ISO 179/1eU |
| Charpy notched impact strength (+23°C) | 5 / - | kJ/m ² | ISO 179/1eA |

Thermal properties

dry / cond

Unit

Test Standard

ISO Data

| | | | |
|---|---------|-------|-----------------|
| Melting temperature (10°C/min) | 222 / * | °C | ISO 11357-1/-3 |
| Glass transition temperature, 10°C/min | 55 / * | °C | ISO 11357-1/-2 |
| Temp. of deflection under load (1.80 MPa) | 80 / * | °C | ISO 75-1/-2 |
| Temp. of deflection under load (0.45 MPa) | 185 / * | °C | ISO 75-1/-2 |
| Coeff. of linear therm. expansion, parallel | 70 / * | E-6/K | ISO 11359-1/-2 |
| Burning behav. at thickness h | HB / * | class | IEC 60695-11-10 |
| Thickness tested | 1.6 / * | mm | IEC 60695-11-10 |
| Oxygen index | 23 / * | % | ISO 4589-1/-2 |

Electrical properties

dry / cond

Unit

Test Standard

ISO Data

| | | | |
|-----------------------------|------------|-------|-------------|
| Relative permittivity, 1MHz | 3.4 / 3.9 | - | IEC 60250 |
| Dissipation factor, 1MHz | 230 / - | E-4 | IEC 60250 |
| Volume resistivity | 1E13 / 1E9 | Ohm*m | IEC 60093 |
| Surface resistivity | * / 1E11 | Ohm | IEC 60093 |
| Electric strength | - / 18 | kV/mm | IEC 60243-1 |
| Comparative tracking index | 600 / - | - | IEC 60112 |

Other properties

dry / cond

Unit


Test Standard

ISO Data


| | | | |
|---------------------|----------|-------------------|----------------|
| Humidity absorption | 3 / * | % | Sim. to ISO 62 |
| Density | 1140 / - | kg/m ³ | ISO 1183 |

Diagrams


Viscosity-shear rate




Shearstress-shear rate



Stress-strain



Stress-strain



Characteristics

Processing

Injection Molding

Other text information

Injection Molding

PROCESSING

Melt temperature: 220°C

Mold temperature: 23°C

Chemical Media Resistance

Acids

- ☺ Acetic Acid (5% by mass) (23°C)
- ☺ Citric Acid solution (10% by mass) (23°C)
- ☺ Lactic Acid (10% by mass) (23°C)
- ⊘ Hydrochloric Acid (36% by mass) (23°C)
- ⊘ Nitric Acid (40% by mass) (23°C)
- ⊘ Sulfuric Acid (38% by mass) (23°C)
- ⊘ Sulfuric Acid (5% by mass) (23°C)
- ⊘ Chromic Acid solution (40% by mass) (23°C)

Bases

-  Sodium Hydroxide solution (35% by mass) (23°C)
-  Sodium Hydroxide solution (1% by mass) (23°C)
-  Ammonium Hydroxide solution (10% by mass) (23°C)

Alcohols

-  Isopropyl alcohol (23°C)
-  Methanol (23°C)
-  Ethanol (23°C)

Hydrocarbons

-  n-Hexane (23°C)
-  Toluene (23°C)
-  iso-Octane (23°C)

Ketones

-  Acetone (23°C)

Ethers

-  Diethyl ether (23°C)

Mineral oils

-  SAE 10W40 multigrade motor oil (23°C)

Standard Fuels

-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)

Salt solutions

-  Zinc Chloride solution (50% by mass) (23°C)

Other

-  Ethylene Glycol (50% by mass) in water (108°C)
-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)
-  Deionized water (90°C)