

TECHNICAL DATA SHEET

Akulon® K224-G8

Envalior
PA6-GF40

Processing

Injection molding

Delivery Form

Pellets

Additives

Release agent

Product Text

Product Information

40% Glass Reinforced

ISO 1043 PA6-GF40

Processing/Physical Characteristics	Value	Unit	Standard
Melt volume-flow rate, MVR	3.2	cm ³ /10min	ISO 1133
Temperature	250	°C	
Load	2.16	kg	
Molding shrinkage, parallel	0.34	%	ISO 294-4, 2577
Molding shrinkage, normal	0.83	%	ISO 294-4, 2577
Density of melt	1259	kg/m ³	
Thermal conductivity of melt	0.32	W/(m K)	
Spec. heat capacity of melt	2080	J/(kg K)	
Eff. thermal diffusivity	1.2E-7	m ² /s	
Mechanical Properties	Value	Unit	Standard
Tensile modulus	13000	MPa	ISO 527
Stress at break	205	MPa	ISO 527
Strain at break	3	%	ISO 527
Poisson's ratio	0.35		ISO 527
Charpy impact strength, +23°C	95	kJ/m ²	ISO 179/1eU
Charpy impact strength, -30°C	85	kJ/m ²	ISO 179/1eU
Charpy notched impact strength, +23°C	14	kJ/m ²	ISO 179/1eA
Charpy notched impact strength, -30°C	10	kJ/m ²	ISO 179/1eA

Akulon® K224-G8




Envalior

Thermal Properties	Value	Unit	Standard
Melting temperature, 10°C/min	220	°C	ISO 11357-1/-3
Temp. of deflection under load, 1.80 MPa	210	°C	ISO 75-1/-2
Temp. of deflection under load, 0.45 MPa	220	°C	ISO 75-1/-2
Coeff. of linear therm. expansion, parallel	20	E-6/K	ISO 11359-1/-2
Coeff. of linear therm. expansion, normal	50	E-6/K	ISO 11359-1/-2
Burning behav. at 1.5 mm nom. thickn.	HB	class	IEC 60695-11-10
Thickness tested	1.5	mm	
Yellow card available	yes		
Burning behav. at thickness h	HB	class	IEC 60695-11-10
Thickness tested	3	mm	
Yellow card available	yes		
Electrical Properties	Value	Unit	Standard
Relative permittivity, 100Hz	3.5		IEC 62631-2-1
Relative permittivity, 1MHz	3.3		IEC 62631-2-1
Dissipation factor, 100Hz	50	E-4	IEC 62631-2-1
Dissipation factor, 1MHz	150	E-4	IEC 62631-2-1
Volume resistivity	>1E13	Ohm*m	IEC 62631-3-1
Surface resistivity	1E13	Ohm	IEC 62631-3-2
Electric strength	35	kV/mm	IEC 60243-1
Comparative tracking index	500		IEC 60112
Other Properties	Value	Unit	Standard
Water absorption	5.5	%	Sim. to ISO 62
Humidity absorption	1.7	%	Sim. to ISO 62
Density	1450	kg/m ³	ISO 1183

Diagrams




Akulon® K224-G8

Envalior




Akulon® K224-G8

Envalior



Akulon® K224-G8

Envalior



Processing Information

Injection molding

Injection Molding Recommendations

Steel recommendations for molds screws and barrels

Trouble shooting guideline for injection molding