



<b>Technyl® C 246M</b>		Solvay Engineering Plastics													
PA6															
<b>Product Texts</b>															
Polyamide 6, unreinforced, with high impact resistance for injection moulding															
<b>Mechanical properties</b>	<b>dry / cond</b>	<b>Unit</b>	<b>Test Standard</b>												
<b>ISO Data</b>															
Tensile Modulus	2000 / 1100	MPa	ISO 527-1/-2												
Charpy notched impact strength (+23°C)	55 / -	kJ/m <sup>2</sup>	ISO 179/1eA												
<b>Thermal properties</b>															
<b>ISO Data</b>															
Melting temperature (10°C/min)	222 / *	°C	ISO 11357-1/-3												
Temp. of deflection under load (1.80 MPa)	60 / *	°C	ISO 75-1/-2												
Burning behav. at thickness h	HB / *	class	IEC 60695-11-10												
Thickness tested	1.6 / *	mm	IEC 60695-11-10												
<b>Electrical properties</b>															
<b>ISO Data</b>															
Relative permittivity, 1MHz	3.5 / 4	-	IEC 60250												
Dissipation factor, 1MHz	200 / -	E-4	IEC 60250												
Volume resistivity	>1E13 / 1E11	Ohm*m	IEC 60093												
Surface resistivity	* / 1E11	Ohm	IEC 60093												
Electric strength	- / 18	kV/mm	IEC 60243-1												
<b>Other properties</b>															
<b>ISO Data</b>															
Density	1080 / -	kg/m <sup>3</sup>	ISO 1183												
<b>Diagrams</b>															
<b>Stress-strain</b>															
<p>Stress-strain Technyl® C 246M(dry)</p> <p>— 23 °C Y - Yield</p> <table border="1"> <caption>Approximate data points from the stress-strain graph</caption> <thead> <tr> <th>Strain (%)</th> <th>Stress (MPa)</th> </tr> </thead> <tbody> <tr><td>0</td><td>0</td></tr> <tr><td>1</td><td>15</td></tr> <tr><td>2</td><td>30</td></tr> <tr><td>3</td><td>40</td></tr> <tr><td>4</td><td>45</td></tr> </tbody> </table>				Strain (%)	Stress (MPa)	0	0	1	15	2	30	3	40	4	45
Strain (%)	Stress (MPa)														
0	0														
1	15														
2	30														
3	40														
4	45														
<b>Characteristics</b>															
<b>Processing</b>															
Injection Molding															
<b>Other text information</b>															

**Injection Molding**

**PROCESSING**

Melt temperature: 220°C

Mold temperature: 50°C

**Chemical Media Resistance**

**Acids**

-  Acetic Acid (5% by mass) (23°C)
-  Citric Acid solution (10% by mass) (23°C)
-  Lactic Acid (10% by mass) (23°C)
-  Hydrochloric Acid (36% by mass) (23°C)
-  Nitric Acid (40% by mass) (23°C)
-  Sulfuric Acid (38% by mass) (23°C)
-  Sulfuric Acid (5% by mass) (23°C)
-  Chromic Acid solution (40% by mass) (23°C)

**Bases**

-  Sodium Hydroxide solution (35% by mass) (23°C)
-  Sodium Hydroxide solution (1% by mass) (23°C)
-  Ammonium Hydroxide solution (10% by mass) (23°C)

**Alcohols**

-  Isopropyl alcohol (23°C)
-  Methanol (23°C)
-  Ethanol (23°C)

**Hydrocarbons**

-  n-Hexane (23°C)
-  Toluene (23°C)
-  iso-Octane (23°C)

**Ketones**

-  Acetone (23°C)

**Ethers**

-  Diethyl ether (23°C)

**Mineral oils**

-  SAE 10W40 multigrade motor oil (23°C)

**Standard Fuels**

-  Standard fuel without alcohol (pref. ISO 1817 Liquid C) (23°C)
-  Standard fuel with alcohol (pref. ISO 1817 Liquid 4) (23°C)

**Salt solutions**

-  Zinc Chloride solution (50% by mass) (23°C)

**Other**

-  Ethylene Glycol (50% by mass) in water (108°C)
-  50% Oleic acid + 50% Olive Oil (23°C)
-  Water (23°C)
-  Deionized water (90°C)